



LABORATORY TEST REPORT

for 9.5mm 35% Bitumen Board Tested as per ASTM D-1751

## 40-BB24-WP

DATA SHEET/TEST REPORT

MANUFACTURER	Jaybro 29 Penelope Cres, Arndell Park NSW 2148 AUSTRALIA
PRODUCT IDENTIFIER	40-BB24-WP Jaybro Bitumen Board Expanion Joint

## PROPERTIES

DIMENSION (thickness)	9.6mm
COMPRESSION	
a. Stress applied for compressing specimen to 50% of its thickness	2195 – 2200 Кра
b. Loss in Weight after application of stress	0.1 – 0.2 %
EXTRUSION	0.10 – 0.11mm
After compressing to 50% of the specimen's thickness	
RECOVERY	84 - 85%
10 minutes after compressing to 50% of the specimen's thickness	
DENSITY	330 – 350 kg/m³
WATER ABSORPTION (%) (by volume)	15%
After 24 hours	
BRITTLENESS	No sign of crack or shatter
DISTORTION	1.5mm
ASPHALT CONTENT	35 – 36%

The information contained herein is accurate to the best of our knowledge. However, It is meant to describe safety requirements of our products, thus this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship. No warranty is expressed or made as to this document's accuracy, reliability or completeness. User has the sole responsibility to determine the suitability of the materials for any use and the manner of use contemplated. The (M)SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered. E&OE.



