

# Petrolatum Tape-Above Ground 75mm x 10m

## Product Images



## Short Description

Above ground petrolatum tape, 75mm x 10m. The 3rd step in the petrolatum process. It is a synthetic, non-stitched, fabric-based tape. Impregnated and coated with petrolatum-based compound and is ideal for protecting pipelines, joints, fittings etc. Often used to waterproof seal joints above and below the ground (2 types, above ground and below ground). Petrolatum tape prevents corrosion even under water.

## Description

- 3rd step in the petrolatum process
- Synthetic, non-stitched, fabric based tape
- Impregnated and coated with petrolatum based compound

- Ideal for protecting pipelines, joints, fittings etc
- Often used to waterproof seal most surfaces above and below the ground (2 types, above ground and below ground)
- Prevents corrosion even under water

## **INSTALLATION OF PETROLATUM TAPE**

RAM PETROLATUM TAPES are extremely surface tolerant and unyielding to moisture, acids, alkalis and salt solutions. RAM PETROLATUM TAPE systems utilize microcrystalline waxes which achieves excellent characteristics including high conformability, superior adhesion / amalgamation to itself and substrates whilst being user friendly to semi skilled applicators.

### **Surface Preparation**

Wire brush dirt, loose rust and foreign matter from surface to be protected. Surfaces should be reasonably dry. On wet surfaces use RAM Marine Primer.

### **Priming**

Apply a thin even film of RAM Primer over the metal surface by gloved hand.

### **Filling**

RAM Moulding Mastic should be used where necessary to improve contours at fittings to achieve a streamline contour. The wrapped fitting with the specified overlap must have no voids, air bubbles and wrinkles.

### **Taping**

Start applying the RAM Petrolatum Tape with a full circumferential turn around the fitting and utilize a nominal 50% overlap to achieve a double thickness of tape. Apply tape ensuring firm tension and then smooth down by hand to exclude any moisture and/or water.

On each new roll of tape, underlap the new roll on previous by a minimum 100 mm.

### **Overwrapping**

RAM High Temperature Outer Wrap should be spirally wrapped (similar to previous procedure) under tension to guarantee contact to achieve a nominal 50% overlap.

## Additional Information

---

CODE	06-PTAG75
U.O.M	Each
Length	10 m
Width	75 mm
Type	Above Ground

