

Fosroc Primer 13 Base 125ml

Product Images



Short Description

Fosroc Primer 13 is designed to be used in conjunction with Fosroc Sealants. Primer 13 is required when working with water immersed applications such as water tanks, sewage works and other applications where the joint will be exposed to moisture for lengthy periods. Primer 13 resists hydrolysis making it ideal for use in immersed applications.

Description

Primer 13 is used to prime prepared concrete joint edges prior to the installation of various Nitoseal joint sealants. Primer 13 resists hydrolysis making it ideal for use in immersed applications such as water tanks, sewage works and other application where the joint will be exposed long term to moisture.

- Mixed material has a pot life of 20 - 30 minutes, and cures to touch dry in an hour
- Note that mixed Primer 13 will remain fluid long after its pot life has expired. Do not use after Pot Life time has passed as the bond strength will be compromised.
- Primer 13 (250ml Pack) consists of a 125ml base and a 125ml hardener
- Primer 13 (1 litre Pack) consists of a 500ml base and a 500ml hardener
- As a guide, 250ml of mixed Primer 13 will prime 15 to 20 meters of a 20 mm deep joint, depending on concrete porosity

For more information, refer to the Technical Data Sheet.

Additional Information

CODE	40-FC965229-125ML
U.O.M	Each
Colour	Amber
Suits Substrate	Concrete
Use With	Fosroc Nitoseal Sealant Range
Box Quantity	12
Brand	Fosroc
Range / Model	Primer Range
Size	125 ml
Appearance / Composition	Multi-Part Mixture
Cure Time	Touch Dry in 1 hour at 23 degrees Celsius
Yield	250ml of mixed Primer 13 will prime 15 to 20m of 20mm deep joint (typical)

