

FOSROC RENDEROC HB40 20KG

Product Images



Short Description

High build repair mortar, conforms to EN1504-3 class R3.

Description

Renderoc HB40 is a high build repair mortar for localised repair of reinforced concrete up to 45MPa. Meets the requirements of EN1504-3 Class R3. It can be applied to vertical concrete patches up to 40 mm deep. Suitable for use with Galvashield anode protection systems.

Additional Information

CODE	40-FC302020-20KG
U.O.M	Each
Suits Substrate	Concrete
Brand	Fosroc
Range / Model	Renderoc
Size	20 kg
Appearance / Composition	Powder
Application Thickness (mm)	10 to 85 mm thickness vertically (70 - 110 mm thickness overhead) when wet sprayed
Cure Time	Initial set in 3 hours, final set in 5 hours
Compressive Strength at 7 days (MPa)	25
Compressive Strength at 28 days (MPa)	38
Yield	Approx 12.9 litres per 20 kg bag
Modulus	18.4 GPa
Swatch	no_selection

