

# FOSROC RENDEROC HB70 20KG

## Product Images



## Short Description

High build repair mortar, conforms to EN1504-3 class R4.

## Description

---

Renderoc HB70 is a high build repair mortar for localised repair of reinforced concrete > 45MPa. Meets the requirements of EN1504-3 Class R4. It can be applied to vertical concrete patches up to 40 mm deep. Suitable for use with Galvashield anode protection systems.

## Additional Information

---

CODE	40-FC303030-20KG
U.O.M	Each
Suits Substrate	Concrete
Brand	Fosroc
Range / Model	Renderoc
Size	20 kg
Appearance / Composition	Powder
Application Thickness (mm)	Up to 100 mm (vertical) and up to 80 mm (overhead) in a single application
Cure Time	Initial set 4 hours, final set 8 hours
Compressive Strength at 7 days (MPa)	45
Compressive Strength at 28 days (MPa)	60
Yield	11.5 litres per 20 kg bag
Modulus	26.9 GPa

