

FOSROC CONBEXTRA GP 20KG

Product Images



Short Description

General purpose, high flow, shrinkage compensated grout.

Description

Conbextra GP is a general purpose shrinkage compensated (Class A) cementitious, flowable or trowellable grout for gap thicknesses from 10 mm up to 100 mm. Conbextra GP has a 28 day compressive strength of 65 MPa when mixed at trowellable consistency.

Additional Information

CODE	40-FC501020-20KG
U.O.M	Each
Pallet Quantity	48
Brand	Fosroc
Range / Model	Conbextra
Size	20 kg
Appearance / Composition	Powder
Application Thickness (mm)	10 to 100 mm
Cure Time	Initial - 5.5 hours, Final - 7.5 hours
Compressive Strength at 7 days (MPa)	50 (stiff) 45 (plastic) 43 (flowable)
Compressive Strength at 28 days (MPa)	75 (stiff) 70 (plastic) 65 (flowable)
Yield	1.6L (stiff) 10.7L (plastic) 10.8L (flowable)
Class	Class A

