

FOSROC CONCURE X90 20L

Product Images



Short Description

Hydrocarbon curing compound.

Description

Concure X90 is a water based hydrocarbon curing compound suitable for curing freshly laid concrete outdoors. Concure X90 will break down if subject to UV exposure and will totally oxidise and leave the surface within 55 days of the application. Concure X90 conforms to AS3799.

Additional Information

| | |
|--------------------------|--|
| CODE | 40-FC600804-20L |
| U.O.M | Each |
| Colour | White |
| Brand | Fosroc |
| Range / Model | Concure |
| Size | 20 L |
| Appearance / Composition | Liquid |
| Cure Time | Tack free in 1 - 3 hours Hard dry in 4 - 8 hours Trafficable in 24 hours |
| Yield | 5 sqm per litre |

