

Surface Cure R-30 Hydrocarbon Resin Emulsion Curing Compound, 1000L

Product Images



Short Description

Surface Cure R-30 is a Hydrocarbon Resin Emulsion Curing Compound (Type 1-D, Class Z). Hot pour asphalt suitable. Also available in other sizes from Jaybro.

Description

Surface Cure R-30 is a liquid applied curing compound which consists of a processed blend of petroleum and resin based hydrocarbons. When applied at the recommended application rate Surface Cure R-30 minimizes moisture loss in freshly laid concrete thus improving the curing of the concrete providing increased strength and durability and improved resistance to surface dusting. Surface Cure R-30 is also available in pigmented variants of white (Type 2- Class B) & black (Type 3- Class B). Mainly used on freshly laid concrete floors, carparks, hardstand areas, warehouses, bridge ramparts etc. Also used for curing vertical concrete areas immediately after the stripping of forms to assist strength development, improve chemical resistance, etc.

Features:

- Hydrocarbon Resin - Water Based - Type 1 D Class Z
- AS3799 Approved / QTMR Approved
- VIC Roads Approved
- RMS Approved
- Rapid film formation time
- Water resistant film formed
- Utilises low VOC formula
- Meets Green Star Rating
- Economical, ease of application reduces labour cost
- Eliminates the need for damp hessian, sand or polythene
- Enables concrete to hydrate more efficiently
- Increases concrete strength and dusting resistance
- Reduces surface shrinkage and cracking
- Odourless when dry

Ideal for:

- Freshly laid concrete floors, carparks, hardstand areas, warehouses, bridge ramparts
- Curing vertical concrete areas immediately after the stripping of forms

APPLICATION

Placement:

Surface Cure R-30 should be evenly sprayed over the freshly laid concrete as soon as possible after trowelling. Ideally Surface Cure R-30 should be applied as soon as the surface bleed water has evaporated.

Certain adhesives for vinyl tiles or other types of resilient flooring and paints of an approved grade may be applied to concrete coated with Surface Cure R-30. It is important however that the concrete should be thoroughly cured prior to such application and that a test area has been completed for approval. Cement based renders and toppings should not be applied over Surface Cure R-30. Refer to the Technical Data Sheet for further information.

Clean Up:

Surface Cure R-30 should be removed from tools and equipment with water if still wet and Solvent 100 or StripSeal if the dry film has formed.

Storage:

Store in cool dry conditions in unopened packs.

Yield:

Covers 5m2 per litre.

Additional Information

CODE	40-CHSCR301000
Weight	1000
Brand	Chemical House
Size	1000 L
Appearance / Composition	Liquid
VOC Content (Volatile Organic Compounds)	Low VOC
Class	Type 1-D, Class Z

